

Property	Unit	Test Method	Specification Limits		Typical Data
			Min	Max	
1 - Function					
Viscosity, 40°C	mm ² /s (cSt)	ISO 3104		12	9.3
Viscosity, -30°C	mm ² /s (cSt)	ISO 3104		1800	1050
Pour point	°C	ISO 3016		-40	-51
Water content	mg/kg	IEC 60814		30	< 20
Breakdown voltage	kV	IEC 60156			
- Before treatment	kV	IEC 60156	30		40-60
- After treatment	kV	IEC 60296	70		> 70
Density, 20°C	kg/dm ³	ISO 12185		0.895	0.875
DDF at 90°C		IEC 60247		0.005	< 0.001
2 - Refining/stability					
Colour		ISO 2049		1.5	< 0.5
Appearance at 15°C		IEC 60296	Clear, Free from Sediment		Clear, Free from Sediment
Acidity	mg KOH/g	IEC 62021		0.01	< 0.01
Interfacial tension at 25°C	mN/m	IEC 62961	40		47
Corrosive sulphur		DIN 51353	Non-Corrosive		Non-Corrosive
Potentially corrosive sulphur		IEC 62535	Non-Corrosive		Non-Corrosive
Corrosive sulphur		ASTM D1275	Non-Corrosive		Non-Corrosive
DBDS	mg/kg	IEC 62697-1	Not Detectable		Not Detectable
Antioxidants	wt %	IEC 60666	Not Detectable		Not Detectable
Metal passivator additives	mg/kg	IEC 60666	Not Detectable		Not Detectable
Other additives *			None		None
2-Furfural and related compounds content	mg/kg	IEC 61198		< 0.05	< 0.05
Aromatic content	%	IEC 60590			9
3 - Performance					
Oxidation stability at 120°C, 164 h		IEC 61125			
- Total acidity	mg KOH/g	IEC 61125		1.2	0.7
- Sludge	wt %	IEC 61125		0.8	0.17
- DDF at 90°C		IEC 61125		0.500	0.041
4 - Health, safety and environment (HSE)					
Flash Point, PM	°C	ISO 2719	135		150
PCA	wt %	IP 346		< 3.0	< 3.0
PCB	mg/kg	IEC 61619	Not Detectable		Not Detectable

*this product contains no undeclared additives

NYTRO LIBRA is an uninhibited insulating oil meeting IEC 60296 Ed. 5 (2020), Type B, TVBU and it is 100% recyclable. Breakdown voltage after treatment as per definition in IEC 60296, section 6,4

Severely hydrotreated insulating oil
 Issuing date: 18-05-2021